

Natural cork stopper H x 24,2 mm

Product description

NORMATIVE

Length	49/44/42/38 mm ± 0,5 mm	UNE 56921
Diameter	24,2 mm ± 0,4 mm	
Ovalization	< 0,5 mm	
Surface treatment	Paraffin and Silicone Elastomer	

Physical and Mechanical Characteristics

NORMATIVE

Humidity	4.0 – 8.0 %	UNE 56921
Density	125-230 Kg/m ³	
Extraction Strength	20 daN – 40 daN	
Capillarity	< 2,5 mm	
Tightness	100 % no leakage at 1.5 bar, in internal Ø 18,5 mm tubes	UNE 56934

Chemical, microbiological and sensory characteristics

NORMATIVE

Oxidising residues (O ₂ ²⁻)	< 0.2 mg / cork stopper	UNE 56929
Sensory analysis	Without sensory desviations	UNE 56928
Fungus and yeasts	< 10 C.F.U / cork stopper	UNE 56921
Aerobic mesophilia bacteria	< 30 C.F.U / cork stopper	
TCA	< 0.5 ng/L	

Recommendations

- Ideal storage temperature between 15 and 25°C, in dry, odor-free and ventilated store.
- Appropriate relative humidity between 50 and 70%.
- Cork stoppers are recommended to be used in a maximum period of 6 months from manufacture date.
- Empty corks feeding hopper after each bottling.
- Do not open the bags until the stoppers are used. Do not leave bags open with leftover corks. Close the bag.
- Cork stoppers should be treated as a food product and should not be stored with chemicals or others giving off odors.
- Processes and products used in their manufacture comply with the International Code of good cork stoppers Practices and EC 2023/2006.



ET.PT.4.2 Rev.11 26/06/2026

C/ Iturrizar, 3 - 31131 CIRAUQUI (Navarra) España
Tel. +34 948 34 21 49 - Fax +34 948 34 21 48
ebro cork@ebro cork.com www.ebro cork.com

ebro cork
C/Iturrizar, 3 - 31131 Cirauqui (Navarra)
Tel. 948 34 21 49 - Fax. 948 34 21 48
ebro cork@ebro cork.com
CIF: B-31742794

BRGS
Packaging Materials
CERTIFICATED

